

**TECHNICAL NOTE****AREMCO-BOND 526N**
CHEMICAL RESISTANCE CHART**IMMERSION, 6 MONTHS** **% WEIGHT GAIN****ACIDS**

Acetic acid, 10%	0.50
Hydrochloric acid, 10%	0.40
Nitric acid, 10%	1.60
Sulfuric acid, 3%	0.15
Sulfuric acid, 10%	-----
Sulfuric acid, 30%	-----

BASES

Ammonia, 25%	-----
Caustic Soda, 1%	0.51
Caustic Soda, 10%	-----
Caustic Soda, 25%	3.00
Sodium Carbonate, 25%	-----

SALTS

Sodium Chloride, 10%	0.30
Sodium Chloride, 25%	-----
Sodium Bisulphate, 10%	-----

ORGANIC FLUIDS

Gasoline	0.15
Benzene	-----
Ethanol	0.15
Ethylene Glycol	0.25
Hydraulic Oil	0.10

WATER

at 25 °C	0.45
at 100 °C	-----